

**PATENT ABSTRACTS OF JAPAN**(11)Publication number : **10-188666**(43)Date of publication of application : **21.07.1998**

(51)Int.Cl.

**H01B 1/12  
C08G 18/48  
C08L 75/08**(21)Application number : **08-340730**(71)Applicant : **ASAHI CHEM IND CO LTD**(22)Date of filing : **20.12.1996**(72)Inventor : **ASAHINA YOSHIYUKI****(54) POLYMER ELECTROLYTE****(57)Abstract:**

**PROBLEM TO BE SOLVED:** To provide high ion conductivity and an excellent mechanical physical property by containing a residual isocyanate monomer reacted with diisocyanate and polyether polyol A at a specific ratio and having specific concentration, polyisocyanate constituted of polyether polyol and isocyanate group, and inorganic salt or ammonium salt.

**SOLUTION:** Aliphatic diisocyanate having the carbon number of 4-30 and polyether A having the hydroxyl group average functional group number of 2-6 preferably react to each other at 60-200° C at the isocyanate group/hydroxyl group equivalence ratio of 5/1-100/1. The concentration of the diisocyanate monomer, polyether polyol A, and isocyanate group in the polyisocyanate obtained after the unreactive diisocyanate and solvent are removed is set to 0-5, 10-98, and 1-20wt.% respectively. The compatibility of the polyisocyanate with the polyether polyol B is improved, and the cross-linking molecular weight of an obtained cross-linking polymer is increased.

**LEGAL STATUS**

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

(19)日本国特許庁 (J P)

(12) 公 開 特 許 公 報 (A)

(11)特許出願公開番号

特開平10-188666

(43)公開日 平成10年(1998) 7月21日

(51)Int.Cl. <sup>6</sup>	識別記号	F I	
H 0 1 B 1/12		H 0 1 B 1/12	Z
C 0 8 G 18/48		C 0 8 G 18/48	Z
C 0 8 L 75/08		C 0 8 L 75/08	

審査請求 未請求 請求項の数3 O L (全 6 頁)

(21)出願番号 特願平8-340730

(22)出願日 平成8年(1996)12月20日

(71)出願人 000000033

旭化成工業株式会社

大阪府大阪市北区堂島浜1丁目2番6号

(72)発明者 朝比奈 芳幸

宮崎県延岡市旭町6丁目4100番地 旭化成  
工業株式会社内

(54)【発明の名称】 ポリマー電解質

(57)【要約】

【課題】 高いイオン伝導性と機械的物性を有する架橋  
ポリマー電解質を提供する。

【解決手段】 ジイソシアネートとポリエーテルポリオ  
ールを反応させ、未反応のジイソシアネートを除去して  
得られ、かつ①残存イソシアネートモノマー濃度0～5  
重量%、②ポリエーテルポリオール濃度10～98重量  
%、③イソシアネート基濃度1～20重量%であるポリ  
イソシアネートと、無機塩またはアンモニウム塩、を含  
むポリマー電解質。